# PRODUCT SPECIFICATION Nitrile Powder Free Examination Gloves (Finger Textured)

## Product Code - NBPFS, NBPFM, NBPFL, NBPFXL

### **SECTION I: PRODUCT DESCRIPTION**

1.1	Туре	Nitrile Examination Glove, Powder Free, Online Single Chlorinated, Non-sterile		
1.2	Material	100% Synthetic Nitrile Latex		
1.3	Color	Blue		
1.4	Design and Feature	Ambidextrous, finger textured, beaded cuff		
1.5	Powder	No powder lubricant added		
1.6	Storage Condition	The gloves shall maintain their properties when stored in a dry condition. Avoid direct sunlight.		
1.7	Shelf-Life	The gloves shall have shelf life of 5 years from the date of manufacture with the above storage condition.		
1.8	Packing Style	100 pcs gloves x 10 dispensers x 1 carton		
1.9	Size Marking	The size of gloves shall be marked in the check box on every carton with black ink.		

# SECTION II : PERFORMANCE REQUIREMENTS

## (Sampling Plan – ISO 2859 Single Normal)

#	Characteristics	Inspection Level	Acceptable Quality Level	Reference Standard
2.1	Dimensions	S2	4.0	ASTM D6319-10 (2015)
2.2	Physical Properties	S2	4.0	ASTM D6319-10 (2015)
2.3	Freedom from Holes (Air Pump Test)	GI	1.5	In-house practice
2.4 (i) (ii)	Visual Defects: Major Visual Minor Visual	GI	2.5 4.0	In-house practice
2.5 (i) (ii) (iii)	Packaging Defects: Regulatory Visual Critical (incl. Gloves Counting)	GI GI S2	** 4.0 4.0	In-house practice
2.6	Powder Free Residue	N=5	-	ASTM D6319-10 (2015) ASTM D6124-06 (2011)
2.7	Mix Size / Mix Glove / Mix Hand	Not	Allowed	

\*\*Unacceptable at any level

### SECTION III: PERFORMANCE SPECIFICATION

#### 3.1 Dimensions

Description	Size	Standard
Length (mm)	All Sizes	Min 240
Palm Width (mm)	XS S M L XL	76 +/- 3 84 +/- 3 94 +/- 3 105 +/- 3 113 +/- 3
Thickness (mm) *single wall	All Sizes	Finger : 0.09 +/- 0.02 (Typical value: 0.08 – 0.11) Palm : 0.07 +/- 0.02 (Typical value: 0.06 – 0.07)

#### 3.2 Physical Properties

Description	Standard		
Description	Before Aging	After Aging	
Elongation at Break (%)	Min 500	Min 400	
Elongation at Dreak (70)	(Typical value: 500 - 600)	(Typical value: 400 – 550)	
Tensile Strength (MPa)	Min 14	Min 14	
Tensne Suengtii (MFa)	(Typical value: 14 – 18)	(Typical value: 14 – 18)	

#### 3.3 Freedom from Holes

The sample size and allowable number of non-conforming gloves in the samples shall be determined in accordance to Sampling Plan ISO 2859-1 Single Normal using inspection and acceptable quality level as stated in Section II: Performance Requirements.

#### 3.4 Visual Defects

The sample size and allowable number of non-conforming gloves in the samples for both major and minor defects shall be determined in accordance to Sampling Plan ISO 2859-1 Single Normal using inspection and acceptable quality level as stated in Section II: Performance Requirements.

#### 3.5 Packaging Defects

The Sample size and allowable number of non-conforming in the samples for regulatory, visual and critical packaging defects shall be determined in accordance to Sampling Plan ISO 2859-1 Single Normal using inspection and acceptable quality level as stated in Section II: Performance Requirements (Gloves Counting=100 pcs by weight per Dispenser).

3.6 Powder Free Residue Maximum 2 mg per glove